



Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China

Product List

	TYPE	MOLE RATIO (St/MAH)	Mw	ACID VALUE KOH/g	Temperature(°C)
Low Molecular Weight SMA	JLSMA-1300	3:1	9000	280	125
	JLSMA-1400	2:1	7500	345	140
	JLSMA-1050	1:1	5000	470	155
	JLSMA-1600	2:1	21000	345	165
	JLSMA-1100	4:1	10000	215	115
	JLSMA-1500	6:1	10000	155	106
	JLSMA-1200	8:1	10000	120	104
	JLSMA-700	1:1	7000	185	60
High Molecular Weight SMA	JLSMA-300	25%MAH	100000- 140000	/	150
	JLSMA-600	18%MAH	120000- 180000	/	135
	JLSMA-540	1.18:1	100000- 180000	230	140-150

Item	TYPE	Structure	Content	MFR/(g/10min)
Polymerized Compatibilizer	JLSMA-100	Styrene, acrylonitrile and maleic anhydride terpolymer	8%MAH	10.0 (200°C,5kg)
	JLSMA-200	Styrene, acrylonitrile and maleic anhydride terpolymer	2%MAH	20.0 (200°C,5kg)