




# Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China  
Contact: +86-18653132120

**Product name: 4,4'-Methylenebis(N,N-diglycidylaniline)**

**CAS: 28768-32-3**

**Molecular weight: 422.52**



Item	Standard
Boiling point	619.3±35.0 °C
Density	1.15 g/mL at 25 °C
Vapor pressure	0Pa at 24.85 °C
Refractive index	n <sub>20</sub> /D 1.601(lit.)
Flash point	>230 °F
LogP	2.12 at 22 °C
Acidity coefficient (pKa)	4.58±0.50



# Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China  
Contact: +86-18653132120

---

## **Application:**

4,4'-Methylenebis(N,N-diglycidylaniline) is applicable for filament winding, pultrusion molding, RTM molding, and other molding processes. 4,4'-Methylenebis(N,N-diglycidylaniline) can be widely used in composite resin, high-temperature resistant adhesive, automobile lightweight, communication cable, military aerospace, rail transit, sports equipment, coating corrosion resistance, and other fields.

## **Package:**

200kg/drum or according to customer requirements.

Unilong Industry