




# Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China  
Contact: +86-18653132120

**Product name: 2,2'-Dithiobisbenzanilide**

**CAS: 135-57-9**

**Molecular Weight: 456.58**



Item	Specification
Boiling point	489.8±30.0 °C(Predicted)
Density	1.1875 (rough estimate)
Melting point	143-146°C
Vapor pressure	0Pa at 25°C
resistivity	1.6360 (estimate)
Storage conditions	2-8°C

## Application:

2,2'-Dithiobisbenzanilide is a plasticizer for natural rubber or styrene butadiene rubber. It should be used at temperatures above 120 °C, especially suitable for high-temperature mixing processing, and should be added at the beginning of plasticization. It does not affect the aging performance of rubber products and does not spray frost. The dosage is 0.05-0.5% in natural rubber and 0.5-3.0% in styrene butadiene rubber.



## Unilong Industry Co., Ltd

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China  
Contact: +86-18653132120

---

### **Package:**

Usually packed in 25kg/drum, and also can be do customized package.

Unilong Industry